

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

BRAYT T1 STRONG POLISHING COMPOUND >silicone free<



PRODUCT DESCRIPTION

BRAYT T1 STRONG it's polishing compound suitable to use on every kind of varnish used in industry and automotive sector, including hard scratch resistant lacquers (also ceramic lacquers). Product recommended for fresh and old paint coatings. Easily removes scratches and traces after P1500 sanding paper. Silicone free, no filler.

PHYSICAL AND CHEMICAL PROPERTIES

- Capacity: 250 g , 1 kg
- Density: approx. 1,23 g/cm³
- Color: white

USAGE

- For hard and scratch resistant varnish use with lambswool or white polishing sponge.
- Apply a small amount of polishing compound on the surface to be polished.
In case of new polishing pad is recommended to apply compound on pad also and make pre polishing.
- Polish using rotary polisher in the optimum speed range 1200 – 1600 RPM (max. 2000 RPM) with slight or medium pressure.
- Polish until all imperfection are removed.
- Remove all residua using microfiber cloth.
- In case of polishing on big surfaces work a small area at time.

STORAGE

TROTON Sp. z.o.o

Address: Ząbrowo 14A, 78-120 Gościno, Poland, Tel: +48 94 35 123 94
Tel/Fax: +48 94 35 126 22 Website: www.troton.com.pl Email: troton@troton.com.pl



January 2016

Product works best when its temperature is 15 – 25⁰C.

Store in close sealed container in temperature 0 - 45⁰C.

EXPIRY DATE

24 months from production date.

All information are based upon the precise laboratory studies and many years of experience. The good market position does not release us from the constant supervision of our products quality. However we are not responsible for the final effects of the improper storage or application of our products, as well as for work inconsistent with the good craft practice.

TROTON Sp. z o.o.
Ząbrowo, Poland

TROTON Sp. z.o.o

Address: Ząbrowo 14A, 78-120 Gościno, Poland, **Tel:** +48 94 35 123 94
Tel/Fax: +48 94 35 126 22 **Website:** www.troton.com.pl **Email:** troton@troton.com.pl